

MINERALOGY AND GEOCHEMISTRY INVESTIGATION OF KUANTAN BAUXITE

MUHAMAD ALIF HILMI BIN MUSTAFA

B. ENG (HONS.) CIVIL ENGINEERING

UNIVERSITI MALAYSIA PAHANG



STUDENT'S DECLARATION

I hereby declare that the work in this thesis is based on my original work except for quotations and citations which have been duly acknowledged. I also declare that it has not been previously or concurrently submitted for any other degree at Universiti Malaysia Pahang or any other institutions.

(Student's Signature)

Full Name : MUHAMAD ALIF HILMI BIN MUSTAFA

ID Number : AA15240

Date : 30th MAY 2019

MINERALOGY AND GEOCHEMISTRY INVESTIGATION OF KUANTAN
BAUXITE

MUHAMAD ALIF HILMI BIN MUSTAFA

Thesis submitted in fulfillment of the requirements
for the award of the
B. Eng (Hons.) Civil Engineering

Faculty of Civil Engineering and Earth Resources
UNIVERSITI MALAYSIA PAHANG

MAY 2019

ACKNOWLEDGEMENTS

All praise and thanks are due to the Almighty Allah who always guides me to the right path and has helped me to complete this thesis. There are many people whom I have to acknowledge for their support, help and encouragement during the journey of preparing this thesis. So, I will attempt to give them their due here, and I sincerely apologize for any omissions

Alhamdulillah, I have managed to complete writing this thesis but of course with the help and support from fantastic people around me. I am deeply grateful to my supervisor, Prof. Madya Dr. Haryati Awang for his guidance, patience and support. I consider myself very fortunate for being able to work with a very considerate and encouraging supervisor like her. I am very indebted to his patience, his trust on my ability and also his invaluable advices that has inspired me to always be positive in completing the report.

My thousand thanks to my family especially to my beloved parents Mustafa Bin Ali and Norlymazita Binti Harun, who been giving me supportive and encouragement me on complete my research. I humbly would like express my gratitude to my collagenous, Syahmi Syafiq Bin Salahuddin and Ahmad Fathiey Bin Razali for been supportive and encourage me throughout the experiment by keep me in high spirit and motivated all the time.

Last but not least, a special thanks to my siblings, for their continuous support and encouragement. I have learned important lessons throughout this research which to never give up and believe in yourself because trust and confidence is the most important value in order to have a successful life.

ABSTRAK

Bauksit adalah batu atau pembentukan tanah yang terdiri terutamanya daripada mineral aluminium hidroksida. Bauksit terutamanya terdiri daripada campuran aluminium hidroksida. Gibbsite, boehmite dan pada tahap yang lebih rendah, diaspora adalah mineral aluminous utama. Komponen lain, penghapusan kepada pengeluaran alumina, adalah tanah liat (terutamanya kaolinit), oksida besi, kuarza, oksida titanium, air dan pelbagai mineral lain (Lozej, 1993). Kawasan bauksit terletak di Kuantan di negeri Pahang. Kawasan bauksit yang terkenal di Bukit Goh, Indera Mahkota dan Semambu. Kajian ini adalah untuk menentukan sifat-sifat geokimia mineral yang terdapat dalam bauksit. Siasatan dijalankan di tiga kawasan yang berlainan di Bukit Goh, Indera Mahkota dan Semambu. Ujian x-ray fluoresens (XRF) dilakukan untuk menentukan sifat-sifat geokimia mineral yang terdapat dalam bauksit di Kuantan. Unsur utama yang diperolehi dari ujian pendarfluor x-ray ialah aluminium (20.5843-25.5384%), besi (15.3052-21.7137%) dan silika oksida (9.0746-15.6503%).

ABSTRACT

Bauxite is a rock or soil formation that is composed primarily of aluminium hydroxide minerals. Bauxite consists primarily of a mixture of aluminium hydroxides. Gibbsite, boehmite and to a lesser extent, diaspore are the main aluminous minerals. Other components, deleterious to alumina production, are clay (mainly kaolinite), iron oxides, quartz, titanium oxide, water and a variety of other minerals (Lozej, 1993). The area of the bauxite lies in the Kuantan in the state of Pahang. The famous area of bauxites at the Bukit Goh, Indera Mahkota and Semambu. This study is to determine the the geochemistry properties of the mineral that contain in the bauxite. An investigation was carried out at three different site which are at Bukit Goh, Indera Mahkota and Semambu. X-ray fluorescence (XRF) test was carried out in order to determine the geochemistry properties of the mineral that contain in the bauxite at Kuantan. The major element that obtained from x-ray fluorescence test are aluminium (20.5843-25.5384%), iron (15.3052-21.7137%) and silica oxide (9.0746-15.6503%).

TABLE OF CONTENT

DECLARATION

TITLE PAGE

ACKNOWLEDGEMENTS **ii**

ABSTRAK **iii**

ABSTRACT **iv**

TABLE OF CONTENT **v**

LIST OF TABLES **viii**

LIST OF FIGURES **ix**

LIST OF ABBREVIATIONS **x**

CHAPTER 1 INTRODUCTION **1**

1.1 Background of Study **1**

1.2 Problem Statement **2**

1.3 Objectives of Study **3**

1.4 Scope of Study **3**

1.5 Significance of Study **4**

CHAPTER 2 LITERATURE REVIEW **5**

2.1 Introduction **5**

2.2 Definition of Bauxite **5**

2.3 The Bauxite Production **7**

2.4 The Bauxite Process to Aluminium **7**

2.5 Chemical Properties of Bauxite **8**

2.6 Geochemistry Tests **9**

| | | |
|---|--|-----------|
| 2.6.1 | Definition of Geochemistry Test | 9 |
| 2.6.2 | The Purpose of Geochemistry Test | 10 |
| 2.6.3 | Type of The Chemical Test for Soil and Rock | 10 |
| 2.7 | Related Studies on The Mineral Element of Bauxites and X-ray fluorescence (XRF) | 13 |
| 2.8 | Gap of Study | 14 |
| CHAPTER 3 METHODOLOGY | | 16 |
| 3.1 | Introduction | 16 |
| 3.2 | Methodology | 16 |
| 3.3 | Materials | 17 |
| 3.3.1 | Soil sampling | 17 |
| 3.3.2 | Disturbed Soil Sample | 18 |
| 3.3.3 | Undisturbed Soil Sample | 18 |
| 3.4 | Methods for test sampling | 19 |
| 3.4.1 | XRF (x-ray fluorescence) | 19 |
| 3.4.2 | The procedure of sampling using handheld XRF | 19 |
| CHAPTER 4 RESULTS AND DISCUSSION | | 23 |
| 4.1 | Mineral of bauxite results using XRF | 23 |
| 4.1.1 | Bukit Goh | 23 |
| 4.1.2 | Indera Mahkota | 27 |
| 4.1.3 | Semambu | 30 |
| 4.2 | Significant mineral of each site | 35 |
| 4.3 | Discussion | 39 |

| | |
|--|-----------|
| CHAPTER 5 CONCLUSION | 40 |
| 5.1 Introduction | 40 |
| 5.2 Conclusion of the Findings | 40 |
| 5.2.1 To determine the mineralogy content of bauxite | 40 |
| 5.2.2 To compare the mineral composition and chemical contents of bauxite in three sites in Kuantan | 40 |
| 5.3 Recommendations | 41 |
| REFERENCES | 42 |
| APPENDIX A | 45 |

LIST OF TABLES

| | | |
|------------|--|----|
| Table 2.1 | Summary of previous study | 14 |
| Table 4.1 | Data 1 of bauxite at Bukit Goh | 24 |
| Table 4.2 | Data 2 of bauxite at Bukit Goh | 25 |
| Table 4.3 | Data 3 of bauxite at Bukit Goh | 26 |
| Table 4.4 | Data 1 of bauxite at Indera Mahkota | 27 |
| Table 4.5 | Data 2 of bauxite at Indera Mahkota | 28 |
| Table 4.6 | Data 3 of bauxite at Indera Mahkota | 29 |
| Table 4.7 | Data 1 of bauxite at Semambu | 30 |
| Table 4.8 | Data 2 of bauxite at Semambu | 31 |
| Table 4.9 | Data 3 of bauxite at Semambu | 32 |
| Table 4.10 | The summary of the results of density element in the bauxite | 33 |
| Table 4.11 | The average results of three sample for each site | 35 |

LIST OF FIGURES

| | | |
|-------------|---|----|
| Figure 1.1 | Bauxite distribution in the world | 2 |
| Figure 1.2 | The location of study area | 4 |
| Figure 2.1 | The location of the bauxite all around the world | 6 |
| Figure 2.2 | The Bayer Process to Produce Aluminium | 8 |
| Figure 2.3 | The example of mineral composition of tropical bauxite | 9 |
| Figure 2.4 | Schematic representation of the different interactions between X-rays and matter | 12 |
| Figure 2.5 | The process of ICP-MS test | 13 |
| Figure 3.1 | The research methodology flow chart | 17 |
| Figure 3.2 | Disturbed soil sample | 18 |
| Figure 3.3 | Hollow pipe use for taking undisturbed soil samples | 19 |
| Figure 3.4 | Labelled the samples according to the location | 20 |
| Figure 3.5 | Place the sample in the special plastic container | 20 |
| Figure 3.6 | Portable handheld XRF | 21 |
| Figure 3.7 | Place the sample on top of steel plate | 21 |
| Figure 3.8 | Close the top lid before testing the sample | 22 |
| Figure 3.9 | Push the ready to test menu for testing the sample | 22 |
| Figure 4.1 | Sample 1 of bauxite from Bukit Goh | 23 |
| Figure 4.2 | Sample 2 of bauxite at Bukit Goh | 25 |
| Figure 4.3 | Sample 3 of bauxite at Bukit Goh | 26 |
| Figure 4.4 | Sample 1 of bauxite at Indera Mahkota | 27 |
| Figure 4.5 | Sample 2 of bauxite at Indera Mahkota | 28 |
| Figure 4.6 | Sample 3 of bauxite at Indera Mahkota | 29 |
| Figure 4.7 | Sample 1 of bauxite at Semambu | 30 |
| Figure 4.8 | Sample 2 of bauxite at Semambu | 31 |
| Figure 4.9 | Sample 3 of bauxite at Semambu | 32 |
| Figure 4.10 | Mineral data of Bukit Goh | 36 |
| Figure 4.11 | Mineral data of Indera Mahkota | 36 |
| Figure 4.12 | Mineral data of Semambu | 37 |
| Figure 4.13 | The comparison of mineral data for three site | 38 |

LIST OF ABBREVIATIONS

| | |
|--------------------------------|--------------------|
| XRF | X-ray fluorescence |
| BG1 | Bukit Goh 1 |
| BG2 | Bukit Goh 2 |
| BG3 | Bukit Goh 3 |
| IM1 | Indera Mahkota 1 |
| IM2 | Indera Mahkota 2 |
| IM3 | Indera Mahkota 3 |
| SM1 | Semambu 1 |
| SM2 | Semambu 2 |
| SM3 | Semambu 3 |
| Al ₂ O ₃ | Alumina |
| Fe | Iron |
| Ti | Titanium |
| SiO ₂ | Silica oxide |
| CaO | Calcium oxide |
| S | Sulfur |
| P ₂ O ₅ | Phosphorus oxide |
| K ₂ O | Potassium oxide |
| Mn | Mangan |
| Zr | Zirconium |
| V | Vanadium |
| Pb | Lead (Plumbum) |
| Nb | Niobium |
| Zn | Zinc |
| Ni | Nickel |
| Bi | Bismuth |
| Cu | Copper |
| Ta | Tantalum |
| Rb | Rubidium |
| Tl | Thallium |
| Cd | Cadmium |
| Y | Yttrium |

| | |
|-----|-----------------|
| Mo | Molybdenum |
| Ce | Cerium |
| Hf | Hafnium |
| Ag | Silver |
| Sr | Strontium |
| MgO | Magnesium oxide |
| Sn | Tin |

CHAPTER 1

INTRODUCTION

1.1 Background of Study

Bauxite is a rock or soil formation that is composed primarily of aluminium hydroxide minerals. In the industrial perspective point of view, Bauxite is considered as a natural material that which can extract alumina from it in a Bayer plant (Lozej, 1993). Bauxite consists primarily of a mixture of aluminium hydroxides. Gibbsite, boehmite and to a lesser extent, diaspore are the main aluminous minerals. Other components, deleterious to alumina production, are clay (mainly kaolinite), iron oxides, quartz, titanium oxide, water and a variety of other minerals (Lozej, 1993)

The way to extracted the alumina from bauxite are through the Bayer process. The procedure of the Bayer process are the ore is mixed with sodium hydroxide and then heat up inside a pressure chamber with temperature of 150 °C to 200 °C until the alumina dissolved and then being filtered out. This process will create waste by-product which is known as bauxite residue or what we called red mud, a heavy metal laden slurry with high alkalinity which can, contain naturally occurring radionuclides at times.

Bauxite can be found all around the world including in Malaysia. Major commercial deposits are found in Australia, China, Brazil, Guyana, Ghana, Guinea, Hungary, India, Indonesia, Jamaica and Suriname (Brown et al., 2015). The existence of bauxite in the Kuantan area, Peninsular Malaysia was first recognized by the Geological Survey in 1937 (Fitch,1952). The area of the bauxite lies in the Kuantan in the state of Pahang. The famous area of bauxites at the Bukit Goh, Indera Mahkota and Semambu. This area can be reach by the new Kuantan bypass that lead toward the highway to Terengganu.




Figure 1.1: Bauxite distribution in the world

1.2 Problem Statement

Bauxite is a controversial issue in Malaysia especially in Pahang. As we know Pahang is the biggest bauxite area in Malaysia. For example, we can see the forests area being cut and levelled in order to explore and to mine the bauxite.

Pahang is a rapidly developing state in Malaysia country. So in a few years, the Kuantan area as the capital of State of Pahang will be developed rapidly and there will be many building and residential area that will be constructed especially at area that we all know contain bauxite deposit.

Other than that, we can see the earth was dug up. If raining, the water runoff will flow to the river and will cause the river water stained red. The water run off contain high amount of mercury and arsenic. This polluted water will harm human in a long term. This is because the water is the important source for the human.

This is important to investigate the chemical content in the bauxite before any construction of the building and residential area. The mineral contents in the bauxite can

affect the building esthetical value which is the colour of the building will become ugly due to the redness colour pollution that may affect the building colour.

Therefore, in order to solve the above problem, this study is carried out to investigate the mineralogy and geochemical of bauxite soil deposits. There are many type of test that we can conduct to determine the chemical content of soil at that area. For this research we conduct the x-ray diffraction method to do testing on the soil samples. The mineral composition is also to be determined.

1.3 Objectives of the Study

This research focus on the mineral content of bauxite. In order to achieve the aim for this research, the following objectives had been established:

- i. To determine the mineralogy content of bauxite.
- ii. To compare the mineral composition and chemical contents of bauxite in three sites in Kuantan

1.4 Scope of the Study

This research will undergo the laboratory test which is X-ray fluorescence test in order to determine and differentiate the mineralogy content that consist in the bauxite. This study is important to determine the mineral content of bauxite because, the bauxite is from various combination. Figure 1.2 show the location of the sample taken for testing from Bukit Goh, Indera Mahkota and Semambu. Three sample will be taken for testing from every site.

REFERENCES

- Moussa Sidibe and Mustafa Gurhan Yalcin, (2018) Petrography, mineralogy, geochemistry and genesis of the Balaya bauxite deposits in Kindia region, Maritime Guinea, West Africa.
- Matthew Stephen Gore (2015) Geotechnical Characterization of Bauxite Residue (Red Mud).
- Gordana Ostojić et.al, (2014) Chemical-mineralogical characterization of bauxites from different deposits.
- Yan Li, Zhaohui Huang and Yan-gai Liu, (2012) Study on Mineral Composition and Main Mineral Morphology of Bauxite from ZhongXiang, HuBei Province.
- Luke J. Kirwan et. al, (2008) Characterisation of various Jamaican bauxite ores by quantitative Rietveld X-ray powder diffraction and Fe Mössbauer spectroscopy.
- Y. Idris, I.I. Funtua, I.M. Umar, (2003) Rapid analysis with energy dispersive X-ray fluorescence spectrometry for bauxite investigation on the Mambilla Plateau, North Eastern Nigeria
- Ali Asghar Calagari, Ali Abedini (2007), Geochemical investigations on Permo-Triassic bauxite horizon at Kanisheeteh, east of Bukan, West-Azarbaidjan, Iran.
- Lance D. Yarbrough et. al (2014) X-ray fluorescence analysis of the Bakken and Three Forks Formations and logging applications
- E. Gordillo-Cruz et. al, (2018), Fractal analysis of X-ray diffraction patterns of zirconia–alumina mixed oxides
- Mark G. Aylmore et. al, (1997) The quantification of lateritic bauxite minerals using X-ray powder diffraction by the Rietveld method

M. Authier-Martin et. al, (2001) The Mineralogy of Bauxite for Producing Smelter-Grade Alumina

Patricia A. Plunkert, (2004) Bauxite and Alumina

Cui, A., Wust, R., Glover, K., Nassichuk, B., (2016). From elemental X-ray fluorescence analyses to reservoir and mechanical properties of unconventional reservoirs: a Montney story. In: AAPG Annual Convention and Exhibition. American Association of Petroleum Geologists, Calgary, Canada 19–22 June.

Murad, E., (2005). Characterization of a standard bauxite and its deferration products by Mössbauer spectroscopy. *Minerals Engineering* 18, 984–986.

Nong, L., Yang, X., Zeng, L., Liu, J., (2007). Qualitative and quantitative phase analyses of Pingguo bauxite mineral using X-ray powder diffraction and the Rietveld method. *Powder Diffraction* 22, 300–302.

Authier-Martin, M., Forte, G., Ostap, S., See, J., (2001). The mineralogy of bauxite for producing smelter-grade alumina. *JOM* 36–40.

Gomes, A.M.D., Vieira, M.B., Santos, N.A., Alves, C.A., (2005). Applied mineralogy studies: an important tool to understand the red mud sedimentation process. *Light Metals* 43–46.

Zamanian, H., Ahmadnejad, F., Zarasvandi, A., (2015). Mineralogical and geochemical investigations of the Mombi bauxite deposit, Zagros Mountains, Iran. *Chemie der Erde – Geochemistry* 76, 13–37.

Zarasvandi, A., Carranza, E.J.M., Ellahi, S.S., 2012. Geological, geochemical, and mineralogical characteristics of the mandan and deh-now bauxite deposits, Zagros fold belt, Iran. *Ore Geol. Rev.* 48, 125–138.

Liu, X.F., Zhu, X.Q., Tang, H.S., Du, S.J., Gu, J., 2018. Geology and geochemistry of the Xiaoshanba bauxite deposit, Central Guizhou Province, SW China: implications for the behavior of trace and rare earth elements, China. *J. Geochem. Explor.* 190, 170–186.

Hanilci, N., 2013. Geological and geochemical evolution of the Bolkardagi bauxite deposits, Karaman, Turkey: transformation from shale to bauxite. *J. Geochem. Explor.* 133, 118–137.